



463-PC417-UV-OR TECHNICAL CHARACTERISTICS



STATIC DISSIPATIVE (CONDUCTIVE) PLASTIC SHEETS WITH UV PROTECTION

TYPE	Polycarbonate
CODE	463-PC417-UV-OR
COLOUR	orange
VERSION	ESD-Standard

ELECTRICAL	METHOD	
Surface Resistivity	ASTM D-257	DIN IEC 60093
Electrostatic Discharge	MIL B-81705B	
Dielectric Constant	ASTM D-150	DIN 53483

UNIT	
Ω / \square	$10^6 - 10^8$
sec	< 0.1
-	3

PHYSICAL		
Specific Gravity	ASTM D-792	DIN 53479
Water Absorption	ASTM D-570	DIN 53495
Pencil Hardness	JIS K 5400	ISO 15184
Adhesion Strength Surface	JIS D 0202	

g/cm ³	1.20
%	0.3
Skala	HB
-	100/100

OPTICAL		
Transmittance (Clarity)	ASTM D-1003	
Refractive Index	ASTM D-542	ISO 489

%	48
-	1.58

MECHANICAL		
Tensile Strength	ASTM D-638	DIN 53455
Tensile Elongation, Break	ASTM D-638	DIN 53455
Flexural Strength, Yield	ASTM D-790	DIN 53452
Flexural Modulus	ASTM D-790	
Compressive Strength	ASTM D-695	
Charpy Impact Strength (23°C)	JIS K 7110	
Notched IZOD Impact Strength	ASTM D-256	

N/mm ²	64.7
%	100
N/mm ²	93.2
N/mm ²	2600
N/mm ²	85.3
kJ/m ²	83.4
J/m	847

THERMAL		
Deflection Temperature	ASTM D-648	
Linear Expansion Coefficient	ASTM D-696	
Heat Conductivity	ASTM C-177	
Specific Heat	ASTM C-177	
Heat Shrinkage	JIS K 6745	
Flammability	UL-94	

°C	135
l/°C	7×10^{-5}
W/mK	0.20
kJ/kgK	1.26
%	
-	

