



ALPERTON Engineering Ltd.

Moyle Road, Dublin Industrial Estate, Glasnevin, Dublin11, Ireland

Phone +353 1 8306277 : Fax +353 1 8306458 : info@alperton.ie : www.alperton.com

Technical Data Sheet

PE300 Black

Product characteristics

- High welding and processing properties
- High chemical resistance
- Suitable for contact with drinking water

Typical field of application

- Chemical engineering and tank building
- Drinking and waste water technology
- Bottling and food industry

	Test method	Unit	Value
General properties			
Density	DIN EN ISO 1183-1	g/cm ³	0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	N/mm ²	22
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	850
Notched impact strength (charpy)	DIN EN ISO 179	kJ/m ²	16
Shore hardness	DIN EN ISO 868	scale D	63
Thermal properties			
Melting temperature	ISO 11357-3	°C	135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ K ⁻¹	150-230
Service temperature, long term	Average	°C	-50 ... 80
Service temperature, short term (max.)	Average	°C	100
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	67
Electrical properties			
Dielectric constant	IEC 60250		2,5
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,0004
Volume resistivity	IEC 60093	Ω *cm	>10 ¹⁴
Surface resistivity	IEC 60093	Ω	>10 ¹²
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV/mm	45

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

All information supplied by or on behalf of Alperton Engineering Ltd in relation to its products, whether in the nature of data recommendations or otherwise is supported by research and believed reliable but Alperton Engineering Ltd assumes no liability whatsoever in respect of application processing or use made of the aforementioned information or products or any consequence thereof. The buyer undertakes all liability in respect of the application processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. No liability whatsoever shall attach to Alperton Engineering Ltd for any infringement of the rights owned or controlled by a third party intellectual industrial or other property by reason of the application processing or use of the aforementioned information or products by the buyer.